

Product Description

CAPILENE® QM 45 F is a polypropylene random copolymer intended for cast film extrusion.

Features:

- Excellent transparency
- High gloss
- Slip and antiblock additives

Uses:

- High clarity films
- Lamination films
- Food packaging
- Injection molded items

Processing Methods:

- Cast film extrusion
- Injection molding

Properties		Method	Typical Value*	Unit
------------	--	--------	----------------	------

Physical

Melt Flow Rate	(230°C/2.16 kg)	ISO 1133	9.5	g/10 min
-----------------------	-----------------	----------	-----	----------

Mechanical

Tensile Stress at Yield	(50 mm/min)	ISO 527-2	23	MPa
--------------------------------	-------------	-----------	----	-----

Tensile Strain at Yield	(50 mm/min)	ISO 527-2	15	%
--------------------------------	-------------	-----------	----	---

Flexural Modulus	(5 mm/min)	ISO 178	900	MPa
-------------------------	------------	---------	-----	-----

Izod Impact Strength, notched	(+23°C)	ISO 180	4	kJ/m ²
--------------------------------------	---------	---------	---	-------------------

Thermal

Vicat Softening Temperature	(10 N)	ISO 306	132	°C
------------------------------------	--------	---------	-----	----

Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	70	°C
------------------------------------	------------	----------	----	----

Optical

Haze	(40 µm film)	ASTM D1003	2	%
-------------	--------------	------------	---	---

*Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance and intended for industrial use, to produce plastic articles. Material safety data sheets, international standards certificates and other regulatory documents are available on our website. Carmel Olefins products have not been tested and therefore not validated for use in pharmaceutical/medical applications, and their suitability for these uses cannot be guaranteed. It is the customer's responsibility to test and approve their technical and regulatory suitability in order to satisfy themselves as to the particular purpose and application(s).